

TECHNICS 5

Flat sponge rubber underlay with high quality reinforced crepe backing and spun-bond polyester scrim facing

Application	Twin stick contract carpet installations; floating and semi-floating wood and laminate installations	
Roll size	11m x 1.37m / 15m ²	12yd x 54" / 18yd ²
Roll weight	41.0kg	90lb (without core)
Core weight	0.7kg	1.6lb
Square weight	2.7kg/m ²	80oz/yd ²
Thickness	5mm	0.200"
Packaging	Brown wrap with blue and red print	



PERFORMANCE TO BS 5808

1 Loss in thickness under static loading	BS4939:1987 / ISO 3416:1986	Less than 5%	1
2 Loss in thickness under dynamic loading	BS4052:1987 / ISO 2094:1987	Less than 5%	1
3 Work of compression [WOC]	BS4098:1975 [2-100kPa]	96J/m ²	1
4 Retained WOC after dynamic loading	BS4098:1975	89%	1
5 Reduction of transmitted impact noise	BS EN ISO 140 Pt8:1998 BS EN ISO 717 Pt2:1997 DIN52210 Part 3	27dB 27dB nominal	4
6 Thermal resistance	BS4745:1990/ISO 5085:Part 1 DIN 52612	0.5 togs 0.05mK/ W	2
7 Effects of small source of ignition, hot metal nut	BS4790:1987/BS5287:1988	Low radius/Pass	1
8 Effects of small source of ignition (Methenamine Pill)	BS6307:1982	Pass	1
9 NBS Radiant panel test	ASTM E648-93A	Pass	3
10 Fire performance of building materials/components	DIN4102 Part 1 and 14	B1	3
11 Epiradiateur test	Norme Francais NFP92-501	M3	5
12 Fire spread and smoke generation *	Nord Test Fire 007:1985	Pass	2

1 Interfloor laboratory result **2** BCTC/WIRA Test House, Leeds, England **3** Warrington Fire Research, Warrington, England

4 Sound Research Laboratory, Sudbury, England **5** SNPE, Vert Le Petit, France * Tested with Brinton's Axminster AX 728


interfloor
INTERFLOOR LIMITED

Interfloor Limited Edinburgh Road Dumfries DG1 1QA United Kingdom
Home sales Tel 08457 600400 Fax 01387 250542
Export sales Tel +44(0)1387 240821 Fax +44(0)1387 250542

Tredaire products do not contain, and are not manufactured using Formaldehyde, CFCs, Heavy Metals, other toxic materials or products from endangered species.
All information contained in this document is correct at the time of going to press. It is the property of Interfloor and may not be reproduced in whole or in part without the consent of Interfloor Limited.